HGY High Temp. Resistance High Silica Glass Fiber Cloth

Description

HGY High Silica Glass Fiber Cloth, made by braided high silica glass fiber, silicon dioxide content ≥96%, is excellent substitute of asbestos cloth and ceramic fiber cloth.



The continuous work temperature can be up to 1000°C, can withstand 1650°C in short time.

The product has high strength, easy to process and width application characteristics, can be used as high temperature, ablation resistance, heat insulation materials.

The product thickness is 0.7mm-1.3mm

Surface coating treatment can be done according to customer's requests.

Application

SiO2 content	≥96%			
Working	Continuous use at 1800°F (1000°C), short term exposure up to			
temperature	3000°F (1650°C).			
Characters	Smooth,soft,extreme high tempt. & flame resistant,high insulation,low			
	friction coefficient ,chemical resistant,avoiding splashing of the			
	molten iron and electric spark.			

Http://: keyuace.en.alibaba.com & www.keyuace.com Email: sales03@keyuace.com
Address: Building B, West Gate, Haoyu Industrial Estate, Shipai, Dongguan, GD523000, P.R. China

Standard Size:



(Shallow Golden Cloth)

PART NO.	Weight	THICKNESS	Width	Length
	(g/m2)	(mm)	(mm)	(m/roll)
HGY-60792G	600		920	
HGY-60710G		0.7	1000	
HGY-607150G			1500	
HGY-91092G	900	1.0	920	46 mater/mall
HGY-910100G		900	1.0	1000
HGY-121392G	1200		920	
HGY-1213100G		1.3	1000	
HGY-1213150G			1500	

(White sintering cloth)



Http//: keyuace.en.alibaba.com & www.keyuace.com Email: sales03@keyuace.com
Address: Building B, West Gate, Haoyu Industrial Estate, Shipai, Dongguan, GD523000, P.R. China



Tel: +86-0769-8173 1593 Fax: +86-0769-8173 2885

PART NO.	Weight (g/m2)	THICKNES (S/mm)	Width (mm)	Length (m/roll)
HGY-650786W	650	0.7	860	FOmtr/roll
HGY-651386W		1.3	000	50mtr/roll



