



Product Technical Data

| Type | Basic W . g/m ² | Thickness mm | Breaking Strength-KN/m | | Stiffness -KN/m | | Air Perm eability mm /s |
|---------|-------------------------------|-----------------|---------------------------|------|-----------------|------|----------------------------|
| | | | MD | CD | MD | CD | |
| 8030 | 30 ±3 | 0.25± 0.03 | >0.8 | >0.5 | >80 | >35 | >5500 |
| 8045 | 45±4 | 0.38±0.04 | >1.0 | >0.8 | >220 | >180 | >5500 |
| 8045-B | 45±4 | 0.38±0.04 | >1.5 | >1.2 | >220 | >180 | >5500 |
| 8050 | 50±5 | 0.45±0.04 | >1.7 | >1.2 | >300 | >200 | >5000 |
| 7050 | 50±5 | 0.34±0.04 | >1.8 | >1.3 | >260 | >200 | >3500 |
| 8060 | 60±6 | 0.48±0.05 | >2.0 | >1.2 | >400 | >250 | >4500 |
| 8060-G | 60±6 | 0.45±0.05 | >2.0 | >1.2 | >400 | >250 | >4500 |
| 8060-DB | 60±6 | 0.45±0.05 | >2.0 | >1.2 | >400 | >250 | >4500 |
| 8070 | 70±7 | 0.5±0.05 | >1.8 | >1.3 | >450 | >300 | >4000 |

| | | | | | | | |
|------|------|-----------|------|------|------|------|-------|
| 8080 | 80±8 | 0.55±0.05 | >2.0 | >1.5 | >550 | >350 | >3500 |
|------|------|-----------|------|------|------|------|-------|

