


ACTMIX MBT-80GN

Accelerator MBT (M)

A C T I V E M A T E R I A L		PROPERTIES:	APPLICATIONS:
		MBT is a quasi-ultrafast, multi-functional accelerator which has longer plateau of vulcanizing period to provide excellent physical and mechanical properties to vulcanizates. It is used as antiscorching agent for sulfurless rubber compounds and as a vulcanization retarder for CR compounds. Alkaline accelerators such as aldehyde-amines and guanidines and thiurams, dithiocarbamates can activate MBT.	Various industrial products such as hoses, conveyor belting, transmission belting, cable jackets.
		DOSAGE:	TYPICAL VALUES:
		Primary accelerator for NR and SBR: 1.0-2.0phr with 2.0-3.0phr sulfur; for IIR: 0.5-1phr with 0.5-1.5 TMTD-80 and 1-2phr sulfur.	Melting point: 170°C
			Purity: Min 98%
			Ash content: Max 0.5%
			Heating loss content: Max 0.3%
			63µm sieve residue: Max 0.5%

M A S T E R B A T C H	PRODUCT	Active Content (%)	Appearance	Filtration (µm)	Binder	Sulfur Content (%)	Density (g/cm ³)
	Actmix® MBT-80GN	80	Light-yellow to yellow Granules	-	NBR	29.5	1.24
	* Binder type can be customized. Except NBR, others binders, such as EPDM/EVM, SBR, AR, ECO also can be available for.						
	SAFETY&TOXICITY:						
	Please refer to related SDS.						
	PACKAGING&STORAGE:						
	Net weight 25kg/PE bags lined carton; Net weight 600kg/pallet.						
	Shelf-life: 1 year in its original packaging						
	Stored in a dry and cool place.						

Compared to traditional MBT powders, Actmix®MBT-80GN allows:

Dust free products with a complete filtration up to 100µm, avoid bitter taste from inhalation, health guard of operators.

Effective guarantee of activity of MBT due to pre-dispersed masterbatch.

Tack free products at room temperature, convenience and accuracy on ingredients.

Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.

Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.

Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.