



Technical Report No. 68.435.17.0703.01
Dated 2017-12-28

Client: Liveon Industrial Co., Ltd

Address: No.46, Yudong 6 Road, the 4th Industrial Estate, Yangdong, Yangjiang, Guangdong, China

Attn.: Mr. David Chen

Sample Description: Stainless Steel Knife

Model No.: /

Supplier: Liveon Industrial Co., Ltd

Sample Received Date: 2017-12-20

Test Period: From 2017-12-20 to 2017-12-27

Test Requested: As specified by client, to test below items as regulated by the German Food & Feed Acts LFGB (§ 30 & 31) and Regulation (EC) No.1935/2004,
1. For material: Metal and Metal alloy
– Specific Migration of 21 Heavy Metals according to European Directorate for the Quality of Medicines & Healthcare Technical guide PA/PH/EMB (13) 9 and Resolution CM/Res(2013)9
2. Sensory test
– With reference to DIN 10955

Conclusion: The submitted sample with test part(s) was found to **comply** with the respective requirement(s) for the tested item(s) as stated in the German Food & Feed Acts LFGB (§ 30 & 31) and Regulation (EC) No.1935/2004 (Material in contact with food regulation)

Test Result: Refer to the following page(s)


Remark: --The result relates only to the items tested.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12&13, Zhiheng Wisdomland Business Park,
Nantou Checkpoint road 2,
Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299

1. TESTED SUBJECT DESCRIPTION

Sample Number	Item Name	Tested Material Description	Photo
001	Stainless Steel Knife	Silvery metal	



This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12&13, Zhiheng Wisdomland Business Park,
Nantou Checkpoint road 2,
Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299

2. TEST RESULT

2.1 SPECIFIC MIGRATION OF HEAVY METAL CONTENT TEST

Test method: The sample(s) were extracted with food simulant , followed by analysis using Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES) and Inductively Coupled Plasma Mass Spectrometry(ICP-MS).

Testing condition and simulant: 0.5% citric acid at 70 °C for 2 hour(s).

No.	Test Item		Result [mg/kg] (3 rd migration)	Limit for 3 rd migration [mg/kg]
			Sample 001	
1.	Barium	(Ba)	<0.1	1.2
2.	Copper	(Cu)	<0.1	4
3.	Iron	(Fe)	0.8	40
4.	Tin	(Sn)	<0.5	100
5.	Chromium	(Cr)	<0.05	0.250
6.	Manganese	(Mn)	<0.1	1.8
7.	Zinc	(Zn)	< 0.1	5
8.	Aluminum	(Al)	<0.1	5
9.	Lithium	(Li)	<0.005	0.048
10.	Beryllium	(Be)	<0.002	0.01
11.	Vanadium	(V)	< 0.002	0.01
12.	Nickel	(Ni)	<0.05	0.14
13.	Cobalt	(Co)	<0.002	0.02
14.	Arsenic	(As)	<0.0004	0.002
15.	Molybdenum	(Mo)	<0.002	0.12
16.	Silver	(Ag)	<0.002	0.08
17.	Cadmium	(Cd)	<0.0004	0.005
18.	Antimony	(Sb)	<0.005	0.04
19.	Mercury	(Hg)	< 0.0005	0.003
20.	Thallium	(Tl)	< 0.0001	0.0001
21.	Lead	(Pb)	< 0.01	0.010

Note:

- “°C” denotes degree Celsius
- “mg/kg” denotes milligram per kilogram foodstuff
- “<” denotes less than.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 TÜV SÜD Group
 Building 12&13, Zhiheng Wisdomland Business Park,
 Nantou Checkpoint road 2,
 Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
 Fax: (86) 755 88285299

Technical Report No. 68.435.17.0703.01
Dated 2017-12-28

(Continued)

Testing condition and simulant: 0.5% citric acid at 70 °C for 2 hour(s).

No.	Test Item		Result [mg/kg] (1 st + 2 nd Migration)	Limit for 1 st +2 nd migration [mg/kg]
			Sample 001	
1.	Barium	(Ba)	<0.2	8.4
2.	Copper	(Cu)	<0.2	28
3.	Iron	(Fe)	3.2	280
4.	Tin	(Sn)	<1.0	700
5.	Chromium	(Cr)	<0.1	1.75
6.	Manganese	(Mn)	<0.2	12.6
7.	Zinc	(Zn)	< 0.2	35
8.	Aluminum	(Al)	<0.2	35
9.	Lithium	(Li)	<0.01	0.336
10.	Beryllium	(Be)	< 0.004	0.07
11.	Vanadium	(V)	< 0.004	0.07
12.	Nickel	(Ni)	<0.1	0.98
13.	Cobalt	(Co)	<0.004	0.14
14.	Arsenic	(As)	<0.0008	0.014
15.	Molybdenum	(Mo)	<0.004	0.84
16.	Silver	(Ag)	<0.004	0.56
17.	Cadmium	(Cd)	<0.0008	0.035
18.	Antimony	(Sb)	<0.01	0.28
19.	Mercury	(Hg)	< 0.001	0.021
20.	Thallium	(Tl)	< 0.0002	0.0007
21.	Lead	(Pb)	< 0.02	0.07

Note:

- “°C” denotes degree Celsius
- “mg/kg” denotes milligram per kilogram foodstuff
- “<” denotes less than.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 TÜV SÜD Group
 Building 12&13, Zhiheng Wisdomland Business Park,
 Nantou Checkpoint road 2,
 Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
 Fax: (86) 755 88285299

2.2 SENSORY TEST

Test method: With reference to DIN 10955: 2004. The submitted sample was treated with food stimulant. After this treatment, treated water was examined by panels with regard to any divergence in smell and taste.

Testing condition and simulant: Distilled water at 70 °C for 2 hour(s)

Test Item	Grading Result	Recommended Level
	Sample 001	
Transfer of Smell	1	< 2.5
Transfer of Taste	1	< 2.5

Note:

- Explanation for grading are listed as below:
Grading 0: No perceptible taste/smell deviation
Grading 1: Just perceptible taste/smell deviation
Grading 2: Weak taste/smell deviation
Grading 3: Clear taste/smell deviation
Grading 4: Strong taste/smell deviation

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:



Jason Peng
Project Handler



Reviewed by:



Vic Wei
Designated Reviewer

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12&13, Zhiheng Wisdomland Business Park,
Nantou Checkpoint road 2,
Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299

APPENDIX:

Photos of submitted products



This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12&13, Zhiheng Wisdomland Business Park,
Nantou Checkpoint road 2,
Shenzhen 518052, P. R. China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299