

## Technical Data Sheet

### XCP-2000D

**Description** XCP-2000D is hydroxyl terminated polyester polyol resulted from adipic acid, diethylene glycol via esterification and polycondensation.

**Properties** Good purity, low color number, good hydroxyl reactivity.

**Applications** XCP-2000D is mainly in use for polyurethanes resins like synthetic leather, elastomers and adhesives.

**Specifications** see below table

Average Mw	2000
Hydroxyl value, mgKOH/g	53~59
Acid value, mgKOH/g	0.2~0.5
Water content, %	<0.03
Status under R.T. (25 °C)	liquid
Functionality	2

**Storage** XCP-2000D has a storage life of 12 months when stored in the original unopened containers with temp. between 5 - 35°C. Opened containers have to be closed immediately and the material should be consumed within a short period. Please also see relevant material safety data sheet for details.

The Information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Suzhou, 2015-07