

CUR 37



Curekind 55P

Composition: Finely selected high molecular weight fatty acid ester emulsion.

Appearance: White or light-color flake

Density: 1.25~1.50g/cm³(20 °C)

Melting point: 55-65 °C

Characteristics Curekind®55P with good heat stability and low volatility under high temperature, good mould

release property and fluidity; 55P can be used as excellent lubricant in plastics and rubber industry; especially, it is suitable for the situation which request high heat stability and good mould release. From the plastic solution in the rubber refining process, and lubrication; excellent nucleating effect of the partially crystalline plastics, can be used for transparent products, an excellent filler and chemical dispersant. Can improve the plasticity of raw rubber, improve the flow properties, increase the injection speed and volume; Make injection and rolling products such as seal products and moulded chip surface smooth, no affect on the vulcanization.

Use: Mixed in the mill and mixer, suggest to add in with the filler to avoid sticky roller. Also can be added by early of mixing, but feed slowly by several times to ensure that the cause can not fight the slippage roll, or it is difficulty to mixing.

Dosage: Used for various moulded or extrusion rubber pars.

NR, IR, SBR, BR, EPDM, CR, ACM: 2~5phr

IIIR, CIIR, IIR, CO/ECO, CSM, EPM: 2~5phr

NBR: 2~4phr

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag.N.W.25kg/bag.
N.W.500kg/pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

Curekind®55P

TECHNICAL DATA SHEET (TDS) version 1.3

Ningbo Actmix Polymer Co., Ltd.

TEL:+86-574-87576736 FAX:+86-574-88002102 Email:dychem@actmix.cn [Http://www.actmix.cn](http://www.actmix.cn)