

Henan Chuange Industry Co., Ltd.

Address: No 73, Beihuan Road, Zhengzhou, China.

Technical Data Sheet

Product:PVC Resin S1000/S700/S1300

TESTING ITEMS	SPECIFICATION (S1000)	SPECIFICATION (S700)	SPECIFICATION (S1300)
Polymerizing Index	1000 +/-50	700 +/-50	1300 +/-50
K - Value	66-68	59-55	72 - 71
Plasticizer absorption of 100g resing \geq	20	14	27
Number of impurity particles \leq	16	16	16
Volatile content (incl. water) % \leq	0.30	0.20	0.20
Apparent density \geq	0.48	0.54	0.45
Particle size	$\geq 0.25\text{mm} \leq$	2.0	2.0
	$\geq 0.063\text{mm} \geq$	95	95
Number of Fish Eye (/400 cm ²) \leq	10	16	10
Whiteness (160°C, after 10 min.) % \geq	78	75	78
VCM Residue PPM \leq	5.0	3.0	5.0