



材料 Material	介質 Medium	工作溫度℃ Temperature	比重	熱膨脹系數	速度 Speed	摩擦系數	抗壓強度
酚醛樹脂	所有潤滑介質	-40至+120	1.1g/cm <sup>3</sup>	$8.3 \times 10^{-5}(k-1)$	≤1m/s	0.15-0.2	3.9N/mm <sup>2</sup>

Model	$\phi D$	$\phi d$
FC	5.6	1.5
FC	5.6	2
FC	5.6	2.5
FC	6	1.5
FC	6	2
FC	6	2.5
FC	6.3	1.5
FC	6.3	2
FC	6.3	2.5
FC	8	1.5
FC	8	2
FC	8	2.5
FC	9.7	1.5
FC	9.7	2
FC	9.7	2.5
FC	10	1.5
FC	10	2
FC	10	2.5
FC	12	2
FC	12	2.5
FC	12.5	2
FC	12.5	2.5
FC	15	2
FC	15	2.5
FC	15	3

Model	$\phi D$	$\phi d$
FC	20	2
FC	20	2.5
FC	20	3
FC	20	4
FC	25	2.5
FC	25	3
FC	25	4
FC	30	2.5
FC	30	3
FC	30	4
FC	35	2.5
FC	35	3
FC	35	4
FC	40	2.5
FC	40	3
FC	40	4
FC	45	2.5
FC	45	3
FC	45	4
FC	50	2.5
FC	50	3
FC	50	4