


# ACTMIX S-80GE F200

## Vulcanizator Sulfur (S)

ACTIVE MATERIAL		<b>PROPERTIES:</b>	<b>APPLICATIONS:</b>
		Sulfur is a vulcanizing agent for natural and dialkene synthetic rubber while it is difficult for traditional sulfur powders to disperse in rubber homogeneously. It is extremely important for light-colored rubber products to use Actmix S-80 due to excellent dispersity to avoid brown-spot appearance and minimize the defects of vulcanizates.	Rubber products exposed to dynamic stress; kinds of soft rubber compounds, sulfur-flawless light-colored rubber compounds.
		<b>DOSAGE:</b>	<b>TYPICAL VALUES:</b>
		0.2-4phr, depending on different use and features.	Melting point: 114°C Purity: Min 99.5% Ash content: Max 0.2% Heating loss content: Max 0.3% 63µm sieve residue: Max 0.5%
		Chemical Formula: S <sub>8</sub> M.W.: 256.52 CAS: 7704-34-9 EINECS: 231-722-6	

MASTERBATCH	<b>PRODUCT</b>	Active Content (%)	Color	Filtration (µm)	Binder	Sulfur Content (%)	Density (g/cm <sup>3</sup> )
	<b>Actmix S-80GE F200</b>	80	Yellow Granules	200	EPDM/EVM	79.5	1.48
	* Binder type can be customized. Except EPDM/EVM, others binders, such as NBR, SBR, AR, ECO also can be available for.						
	<b>SAFETY&amp;TOXICITY:</b>						
	Please refer to related SDS.						
<b>PACKAGING&amp;STORAGE:</b>							
Net weight 25kg/PE bags lined carton; Net weight 600 or 750 kg/pallet.							
Shelf-life : 1 year in its original packaging							
Stored in a dry and cool place.							

### Compared to traditional S powders, Actmix S-80GE F200 allows:

Dust free products with a complete filtration up to 63µm, no skin sensitization, avoidance of burning or even explosion when mixed with air.

Effective guarantee of stability and activity of sulfur due to pre-dispersed masterbatch.

Tack free products at room temperature, convenience and accuracy on ingredients.

Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion, no appearance of brown-spot.

Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.

Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder, F200: filtration and micron number of filter

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.