

## Curekind ZBPD/S

|  |   |                                  |  |
|--|---|----------------------------------|--|
| <b>D<br/>E<br/>S<br/>C<br/>R<br/>I<br/>P<br/>T<br/>I<br/>O<br/>N</b> | Zinc O,O',O',O'-tetrabutyl<br>bis(phosphorodithioate) | Items                            | 75% Zinco,o-dibutylDithiophosphate<br>bounded 25%SiO2 - Powder |
|  | C28H60O4P2S4Zn  | Appearance                       | Light white Powder   |
|  | M.W.: 716.39  | Assay,%                          | 73.5-76.5  |
|  | CAS NO.6990-43-8                                      | Sulfur,%                         | 15.5-17.5  |
|  | E/C NO.230-257-6                                      | 25°C Density(g/cm <sup>3</sup> ) | 1.30   |

**Characteristics** Curekind ZBPD/S, a fast curing secondary accelerator for NR and EPDM.

**Application** Curekind ZBPD/S mainly used as vulcanizing accelerator for

EPDM,non-blooming,lower cost and fast curing rate.Because of non-amine based structure,Curekind ZBPD/S can be used to non-Nitrosamine formed curing systems.

Curekind ZBPD/S is regulated for use in articles in contact with food as specified under BgVV.XXI, category4,and id not regulated for use in FDA food contact applicants.

**Safety and Toxic** Refer to the MSDS

**Storage** Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

**Package** Carton lined with PE plastics bag. N.W. 25kg/carton, N.W.600kg / pallet.  
Shelf-life: 24 months in its original packing.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.