


# ACTMIX TBzTD-70GR

## Accelerator TBzTD

ACTIVEMATERIAL



C<sub>30</sub>H<sub>28</sub>N<sub>2</sub>S<sub>4</sub>  
 M.W.: 554.82  
 CAS: 10591-85-2  
 EINECS: 404-310-0

### PROPERTIES:

TBzTD can lead to high processing safety and faster cure rate as an accelerator of natural rubber and synthetic rubber vulcanization. TBzTD satisfies requirements of "Technical Regulations for Dangerous Materials" TRGS 552 about toxicity of nitrosamines in Germany and not release carcinogenic nitrosamines during vulcanization. Addition of thiazoles or sulfenamides accelerators can slow the vulcanization, shorten scorching and vulcanization time and vulcanization without significant increases. It can be activated by alkaline accelerators such as aldehyde-amines and guanidines.

### DOSAGE:

0.2-2.0phr with 0.9-2.8phr sulfur.

### TYPICAL VALUES:

Melting point: Min 128°C  
 Purity: Min 96%  
 Ash content: Max 0.3%  
 Heating loss content: Max 0.3%  
 63µm sieve residue: Max 0.5%

MASTECH

PRODUCT	Active Content (%)	Appearance	Filtration (µm)	Binder	Sulfur Content (%)	Density (g/cm <sup>3</sup> )
<b>Actmix TBzTD-70GR</b>	70	Light-Yellow Granules	-	IR	16.4	1.12

\* Binder type can be customized. Except SBR, others binders, such as NBR, EPDM/EVM, AR, ECO also can be available for.

### SAFETY&TOXICITY:

Please refer to related SDS.

### PACKAGING&STORAGE:

Net weight 25kg/PE bags lined carton; Net weight 600 kg/pallet.

Shelf-life: 24 months in its original packing.

Stored in a dry and cool place.

### Compared to traditional TBzTD powders, Actmix TBzTD-70GR allows:

Dust free products with a complete filtration up to 100µm, no skin sensitization, health guard of operators.

Effective guarantee of activity of TBzTD due to pre-dispersed masterbatch.

Tack free products at room temperature, convenience and accuracy on ingredients.

Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.

Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.

Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.