ESCRIPTI



Curekind ZEPC(PX)

\
NA Znt I I I
* 1 2 S
(
Zina Ethul Dhanl Dithia asuba

Zinc Ethyl Phenl Dithiocarbamate

 $C_{18}H_{20}N_2S_4Zn$ M.W. 458.02

CAS No.: 14634-93-6 EINECS No.: 238-677-1

lto ma	Specification
<i>Items</i>	Powder
Appearance	White or light yellow Powder
Initial Melting Point, ℃min.	195.0
Heat Loss,% max.	0.50
Ash Content,% max.	24.0
Density, g/cm ³	1.5
Residue on 150µm,% max.	0.10
Residue on 63µm,% max.	0.50

CharacteristicsCurekind ZEPC is white or light-yellow poser, inodorous, non-toxic, soluble in hot benzene, hot chloroform, insoluble in alcohol and water, a little soluble in gasoline and benzene.

Application Curekind ZEPC, super accelerator, excellent anti-scorching performance, suitable for vulcanizing of latex. Curekind ZEPC, non-toxic, inodorous, stainless and non-discolouring on products, suitable for coated fabric,. Medical supplies, Latex Model Products, Impregnation products, Latex Sponge, Tape, sulfur mortar etc.

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag;N.W.500kg/pallet. Shelf-life: 24 months in its original packing.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

CurekindZEPC(PX)

TECHNICAL DATA SHEET (TDS) version 1.3

Ningbo Actmix Rubber Chemicals Co., Ltd.