


Curekind TeDEC(TDEC)

DESCRIPTION	Items	Specification	
		Powder	Dust free Powder
 <p>Tellurium Diethyl Dithiocarbamate $C_{20}H_{40}N_4S_8Te$ M.W. 721 CAS No.: 20941-65-5 EINECS No :244-121-9</p>	Appearance	Light-orange to yellow powder	
	Initial Melting Point, °C min.	105.0	100.0
	Heat Loss, % max.	0.50	0.50
	Tellurium Content, %	16.5-19.0	16.5-19.0
	Density, g/cm ³	1.48	1.48
	Residue on 150µm, % max.	0.10	0.10
	Residue on 63µm, % max.	0.50	0.50
	Additive, %	-	1.0-2.0

Characteristics Curekind TDEC is Light-orange to yellow Powder. Soluble in chloroform, benzene, and carbon disulfide, a little soluble in alcohol and gasoline, insoluble in water.

Application Curekind TDEC, a super vulcanizing accelerator for natural rubber, styrene-butadiene rubber. Suitable for making inner tube of tires, soft tube, isolating layer of wire and cable, etc.. Curekind TDEC is regulated for use in articles in contact with food as specified under BgVV XXI, Category 4.

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag;N.W.500kg/pallet.
Shelf-life: 24 months in its original packing.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.