



Product Data Sheet

Metallised BOPP (TC)/Water Based Permanent/ White Glassine 71QL0922

Facestock

Metallised BOPP

A bright metallised bi-axially oriented polypropylene film with printable coating.

| | | |
|--------------|--------------------------------|---------|
| Color | / | |
| Basic Weight | 45 (± 2)g/m ² | ISO-536 |
| Thickness | 50(± 2) μ | ISO-534 |

Adhesive

Water based permanent

A water based acrylic permanent adhesive providing good tack and adhesion to a wide variety of substrates including apolar surfaces. Complies with FDA 175.105, recommend on dry and non fatty foodstuffs.

| | | |
|-------------------|----------------|------|
| Initial Tack | 8 N/25mm | FTM9 |
| Peel adhesion 90° | 6 N/25mm | FTM1 |
| Min.Appl.Temp. | +5 °C | |
| Service Temp. | -10 °C to 80°C | |

Liner

One side siliconised glassine

| | | |
|--------------|--------------------------------|---------|
| Color | White | |
| Basic Weight | 60 (± 2)g/m ² | ISO-536 |
| Thickness | 50 (± 2) μ | ISO-534 |

Application

This material is resistant to moisture and grease, suitable for wide range of purposes including eye-catching promotional identification labels for cosmetics, perfumes and beverages.

Printing Methods

Provides very good printability on most conventional printing technologies including UV flexo, UV letterpress and UV offset.

Shelf life

- 1 year if stored at following condition:
- Store in a cool and dry place, and keep the material in original packaging when not used.
 - Temperature 23 \pm 2°C .
 - Humidity 50 \pm 5%.
 - Keep away from direct sunlight.

• The above data has been typically tested in our own laboratory but it does not represent as guarantee of all purpose. In order to ensure the correct usage of our products, further testing on the corresponding substrates to verify the result is always recommended.