

Client	Liveen Industrial Co. Ltd			
Client:	Liveon Industrial Co., Ltd.			
Address:	No. 46, Yudong 6 Road, the 4 th Industrial Estate, Yangdong, Yangjiang, Guangdong, China			
Attn.:	Mr. David Chen			
Sample Description:	Golden titanium coating knife, color coating knife with sheath, uncoated s/s knife, color coating knife			
Model No.:	006314, 0081128, 004302-06, 006220-27			
Country of origin:	China			
Exported to:	U. S. A			
Sample Received Date:	2016-05-24			
Test Period:	From 2016-05-24 to 2016-06-02			
Test Requested:	 Test for compliance with U.S. F.D.A. C.F.R. 21. Part 175.300 (for resinous and polymeric coatings in contact with food) With reference to U.S. F.D.A. C.F.R. 21. Part 175.300 			
	 Test for compliance with U.S. F.D.A. CPG 7117.05-Section 545.500 Leachable Lead with reference to ASTM C738-94 			
Test Results:	Refer to following page(s)			
Conclusion:	 The submitted sample 001 was found to comply with the respective requirement(s) for the tested item(s) as specified in U.S. F.D.A. C.F.R. 21. Part 177.1500 for nylon resins in contact with food. 			
	 The submitted sample 002 and 003 were found to comply with the General Recognized As Safe (GRAS) Specifications for US FDA regulation on for Stainless steel in contact with food 			



1. TESTED SUBJECT DESCRIPTION

Sample Number	Item Name	Tested Material Description	Photo
001	Coating	Black coating	NN
002	Blade	Coppery metal	
003	Blade	Silvery metal	



TEST RESULTS 2.

2.1 TEST FOR COMPLIANCE WITH U.S. F.D.A. C.F.R. 21. PART 175.300

Test Item	Result [mg/in ²]	CFR Specification	
reschem	Sample 001	[mg/in ²]	
Total extractives in distilled water (212°F for 0.5 hour)	< 1.0	18	
Total extractives in 8% ethanol (212°F for 0.5 hour)	< 1.0	18	
Total extractives in n-Heptane (120°F for 0.5 hour)	< 1.0	18	

Note:

- "mg/in²" denotes milligram per square inch
 "°F" denotes degree Fahrenheit

- "<" denotes less than

- Specification is quoted from U.S. F.D.A. C.F.R. 21. Part 175.300



2.2 TEST FOR COMPLIANCE WITH U.S. F.D.A. CPG 7117.05 - Section 545.500

Test Item		Result(s) [µg/ml]		CPG Specification
		Sample 002	Sample 003	[µg/ml]
Leachable Lead	Trial 1	< 0.10	< 0.10	
	Trial 2	< 0.10	< 0.10	Average of 6 units < 7 ug/ml
	Trial 3	< 0.10	< 0.10	
	Trial 4	< 0.10	< 0.10	
	Trial 5	< 0.10	< 0.10	
	Trial 6	< 0.10	< 0.10	
	Average	< 0.10	< 0.10	

Note :

- "ug/ml" denotes microgram per milliliter.

— "<" denotes less than</p>

- Specification is quoted from U.S. F.D.A. CPG 7117.05 - Section 545.500.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch TÜV SÜD Group

Prepared by:

Xm

Jerry Xin Project Handler Reviewed by:

indert

Scarlett Liang Designated Reviewer

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch TÜV SÜD Group Building 12&13, Zhiheng Wisdomland Business Park, Nantou Checkpoint road 2, Shenzhen 518052, P. R. China Tel.: (86) 755 88286998 Fax: (86) 755 88285299



APPENDIX:

Photos of submitted products



Page: 5 of 5