



HENAN SHUNBANG CHEMICAL CO., LTD

NO.85 Huayuan Road, Jinshui District, Zhengzhou City, Henan Province, China

TEL:+86-371-65582722

FAX:+86-371-65582722

Technical Data Sheet

Standard: GB/T5761-2006	PVC Resin SG5				
		index value			Test Result
		top quality	first Grade	qualified	
K-Value		68-66			
Appearance		white powder			
Viscosity numbers		118-107			110
Numbers of impurity particles (per 100g)	≤	16	30	80	14
Volatile content (including water)%	≤	0.40	0.40	0.50	0.12
Apparent density (g/ml)	≥	0.48	0.45	0.42	0.545
0.25mm Residue on sieve %	≤	2.0	2.0	8.0	0.6
0.063mm Residue on sieve %	≥	95	90	85	99.2
Numbers of Fish-eye (per 400cm ²)	≤	20	40	90	11
Adsorption amount of plasticizer (g/100g)	≥	19	17	--	24
Whiteness (160°C, 10minutes)%	≥	78	75	70	80.1
Residue VCM content (μg/g)	≤	5	10	30	1