

### Features

- ★ Long survives life: ultra particle composite silicate solution is neutral, not corrode plates inside the battery, survive life is up to 15years standby use.
- ★ It will not generate gas in use, the electrolyte is neutral, so it can reduce environmental pollution. The engine Room need no ventilation, explosion-proof, the floor need no acid proof pipeline need not to buried specially, thereby reducing the total cost of the enterprise investment.

### Applications

- ★ Solar system and Wind system
- ★ Solar street light and solar garden light
- ★ Emergency lighting equipment
- ★ Fire alarm and security systems
- ★ Telecommunication equipment
- ★ Electric equipment and telemeter equipment

Nominal Voltage		12V
Nominal Capacity (20 hour rate)		80Ah
Capacity 25°C (77°F)	10 hour rate (7.2A)	72Ah
	5 hour rate (12.7A)	63.5Ah
	1 hour rate (46.7A)	46.7Ah
Internal Resistance	Full Charged Battery 25°C	≤6.0m Ω
Capacity affected by Temperature (10 hour )	40°C (104°F)	102%
	25°C (77°F)	100%
	0°C (32°F)	90%
	-15°C (5°F)	75%
Self-Discharge 25°C (77°F) Capacity	after 3 month storage	92%
	after 6 month storage	84%
	after 12 month storage	75%
Charge (Constant Voltage) 25°C (77°F)	Float	Initial Charging Current Less than20.0A Voltage 13.6-13.8V
	Cycle	Initial Charging Current Less than20.0A Voltage 14.4-14.9V

Battery Dimensions	Length	260mm
	Width	169mm
	Height	211mm
	Total Height	215mm
Box Dimensions	Length	275mm
	Width	183mm
	Height	272mm
Quantity Per Box		1 PC per box
Net weight Per Cell		24.5 kg±200g
Net weight Per Box		24.5kg
Gross Weight		25.0kg





### Discharge Constant Current (Amperes at 77°F25°C)

F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	201.2	125.1	103.8	73.3	52.6	46.7	28.9	19.8	13.5	8.9	7.9	4.4
1.65V	197.5	122.9	101.9	71.9	51.6	45.9	28.4	19.4	13.2	8.7	7.8	4.3
1.70V	193.9	120.6	100.0	70.6	50.7	45.0	27.9	19.1	13.0	8.5	7.6	4.2
1.75V	190.2	118.3	98.1	69.3	49.7	44.2	27.3	18.7	12.7	8.4	7.5	4.1
1.80V	182.9	113.8	94.3	66.6	47.8	42.5	26.3	18.0	12.2	8.1	7.2	4.0

### Discharge Constant Power (Watts at 77°F25°C)

F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	387.2	240.9	199.7	141.0	101.2	90.0	55.6	38.1	25.9	17.1	15.2	8.4
1.65V	380.2	236.5	196.1	138.5	99.4	88.3	54.6	37.4	25.4	16.8	15.0	8.2
1.70V	373.2	232.1	192.5	135.9	97.6	86.7	53.6	36.7	25.0	16.5	14.7	8.1
1.75V	366.1	227.7	188.8	133.3	95.7	85.0	52.6	36.0	24.5	16.1	14.4	7.9
1.80V	352.0	219.0	181.6	128.2	92.0	81.8	50.6	34.7	23.6	15.5	13.9	7.6

## Performance Characteristics



## Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Si-Rubber	Copper	Fiberglass	GEL

