


# ACTMIX CTP-50GS

## Anti-Scorcher CTP (PVI)

A  
C  
T  
I  
V  
E  
  
M  
A  
T  
E  
R  
I  
A  
L



Cyclohexylthiophthalimide

C<sub>14</sub>H<sub>15</sub>O<sub>2</sub>SN

M.W.: 261.34

CAS: 17796-82-6

EINECS: 241-774-1

### PROPERTIES:

Active ingredient CTP is a vulcanization retarder of nature rubber and diene rubbers, which can unnoticeably prolong total vulcanizing time. It can improve processing safety and not impact properties of vulcanizates combination with sulfenamides or thiazoles. This product can significantly improve the storage stability and high temperature processing safety performance of unvulcanized rubber, fully improve equipments production capacity. It does not cause a contact stain.

### DOSAGE:

Usually 0.2-2.0phr, will be blooming if more than

5.0phr.

### APPLICATIONS:

Nature and synthetic rubber compounds ( tyre, conveyor belt, shoe soles, molded and extruded products).

### TYPICAL VALUES:

Melting point: 89°C

Purity: Min 98%

Heating loss: Max 0.5%

Ash content: Max 0.1%

### CAUTIONS:

Non-staining, little colored for white rubber compounds.

M  
A  
S  
T  
E  
R  
B  
A  
T  
C  
H

PRODUCT	Active Content (%)	Appearance	Filtration (µm)	Binder	Sulfur Element (%)	Density (g/cm <sup>3</sup> )
<b>Actmix® CTP-50GS</b>	50	White Granules	-	SBR	5.6	1.30

\* Binder type can be customized. Except SBR, others binders, such as EPDM/EVM, NBR also can be available for.

### SAFETY&TOXICITY:

Please refer to related SDS.

### PACKAGING&STORAGE:

Net weight 25kg/carton lined PE bag; Net 600 kg/pallet.

Shelf-life : 1 year in its original packaging

Stored in a dry and cool place.

### Compared to traditional CTP powders, Actmix®CTP-50GS allows:

Dust free products with a complete filtration up to 150µm, avoid bad odor of CTP, health guard of operators.

Effective guarantee of activity of MBI due to pre-dispersed masterbatch.

Tack free products at room temperature, convenience and accuracy on ingredients.

Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.

Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.

Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

Actmix®CTP-50GS

TECHNICAL DATA SHEET (TDS) version 1.3

## Ningbo Actmix Rubber Chemicals Co.,Ltd.

TEL: +86-574-87468726 FAX: +86-574-88002102 Email: dychem@actmix.cn Http://www.actmix.cn